



# TYPE APPROVAL CERTIFICATE

Certificate no.:  
**TAK00001TH**  
Revision No:  
**1**

---

**This is to certify:**

**that the Glass Fibre Products**

with type designation(s)

**Woven Rovings: EWR270, EWR360, EWR500, EWR580, EWR600 and EWR800**

issued to

**Jushi Group Co., Ltd.**



Job ID: 262.1-031276-2  
Certificate no.: TAK00001TH  
Revision No: 1

## Product description

Woven Rovings: **EWR270**, **EWR360**, **EWR500**, **EWR580**, **EWR600** and **EWR800**.

### Legends:

E: E-Glass

WR: Woven Roving

270, 360, 500, 580, 800: Weight per unit area, g/m<sup>2</sup>

The following indicative properties have been verified by Type Testing of laminates:

| Properties                             | Test Method                               | EWR270                  | EWR360                  | EWR500                  |      |     |
|----------------------------------------|-------------------------------------------|-------------------------|-------------------------|-------------------------|------|-----|
| Tensile Strength – warp                | ISO 527-1,4                               | 409.04                  | 425.57                  | 457.28                  | mean | MPa |
| Tensile Modulus – warp                 | ISO 527-1,4                               | 24.04                   | 25.28                   | 22.80                   | mean | GPa |
| Tensile Strength – weft                | ISO 527-1,4                               | 395.67                  | 350.77                  | 440.20                  | mean | MPa |
| Tensile Modulus – weft                 | ISO 527-1,4                               | 23.70                   | 23.65                   | 24.17                   | mean | GPa |
| Fibre content by weight                | ISO 1172                                  | 61.13 (0)<br>61.89 (90) | 61.16 (0)<br>61.22 (90) | 61.65 (0)<br>61.32 (90) | mean | %   |
| Resin                                  | TM-107                                    |                         |                         |                         |      |     |
| Curing Procedure used for Type Testing | 24 hrs at room temperature, 4 hrs at 80°C |                         |                         |                         |      |     |

| Properties              | Test Method | EWR580 | EWR600 | EWR800 |      |     |
|-------------------------|-------------|--------|--------|--------|------|-----|
| Tensile Strength – warp | ISO 527-1,4 | 459.29 | 511.93 | 440.15 | mean | MPa |
| Tensile Modulus – warp  | ISO 527-1,4 | 24.77  | 26.62  | 23.53  |      |     |

